



# LEADERS IN WAX TECHNOLOGY

THE FINEST NATURAL WAXES IN THE WORLD SINCE 1904

## CERESINE WAX SPECIFICATIONS

White Ceresine Wax		
S&P Number	Melting Point	Penetration 100/25 Deg. C/5
SP-248	58.3°C – 61.7°C	7-13
SP-251	60.0°C – 65.6°C	8-18
SP-252	53.9°C – 57.2°C	10-15
SP-254	62.7°C – 67.8°C	9-15
SP-272	54.4°C – 57.8°C	12-18
SP-301	71.1°C – 74.4°C	9-15
SP-309	54.4°C – 57.2°C	8-14
SP-931	54.4°C – 57.2°C	10-15
SP-1022C	62.8°C – 65.6°C	8-13
SP-2931 *	68.3°C – 76.7°C	6-15
* COLIPA COMPLIANT		