



LEADERS IN WAX TECHNOLOGY

THE FINEST NATURAL WAXES IN THE WORLD SINCE 1904

MICROCRYSTALLINE WAX SPECIFICATIONS

Microcrystalline Wax			
	Melting Point	Penetration 100/25 Deg.C5	Color
SP-16 *	79.4°C - 86.7°C	15-22	Yellow
SP-16W *	79.4°C - 86.7°C	15-22	White
SP-18 *	73.9°C - 79.4°C	55-75	White
SP-19 *	76.7°C - 82.3°C	25-35	White
SP-26	76.6°C - 82.3°C	25-35	Yellow
SP-60	79.4°C - 85°C	16-22	Yellow
SP-88	87.8°C - 96.1°C	3-10	White
SP-97	70.0°C – 74.4°C	25-35	Off-White
SP-617	88.3°C - 92.8°C	8-14	Yellow
SP-623	87.8°C - 96.1°C	5-10	Off-White
* COPILA COMPLIANT			
FDA approved under 21 CFR 172.886, 172.3710, Japanese Name/ Source – Microcrystalline Wax / JSCI			