



LEADERS IN WAX TECHNOLOGY

THE FINEST NATURAL WAXES IN THE WORLD SINCE 1904

DATA SHEET

PETROLEUM BASED

S & P Number	Name	Description	Melting Point ASTM D-127	Congeaing Point ASTM D-938	Needle Penetration ASTM D-1321 @ 77°F
SP-1792	Single pour container blend.	Standard one pour container blend. Good adhesion to glass and moderate fragrance loading.	135	156	12
SP-124	Satin finish pillar blend	High performing blend with a unique "satin" finish and excellent release.	160	122	49